

**ABSTRACT OF THE DISCLOSURE**

Spun bond is made by collecting thermoplastic filaments on a perforated surface and the spun bond is then subjected to hydrodynamic consolidation with high-pressure water jets. The filaments before the formation of the spun bond or after the formation of the spun bond are treated with a wetting agent prior to the hydrodynamic consolidation.

ef-